



????????? ??????????????????			
????????????? ??????????	??????????	??????	?????
????????????? ??? ?/??	0,850	DIN 51 757	
15°?			
????????????? °C	230	DIN 2592	
??????????			
????????????, ??? ???*?	5100	ASTM D 5293	
-30°C (CCS)			
??? ??*/c	67	DIN 51 562	
40°C (CCS)			
??? ??*/c	11,7	DIN 51 562	
100°C (CCS)			
????????? ???????????	175	DIN 2909	
????????????? ?? % ?????.	7,7	ASTM D 5880	
NOACK, 1?, 250°?			

????????????? ??? ??????????????

[?????????? TITAN GT1 PRO FLEX 23 5W-30.pdf](#)

??????????

????????? ?????????? ?? ??? ???? ???? ?? ??????????